

Solargard® Rust Primer WB

Acrylic metal primer

FEATURES

Water-based acrylic formulation

Metal primer formulation

BENEFITS

- Easy clean up
- Tough and flexible
- Prevents corrosion on metal substrates
- Provides protection against rust

DESCRIPTION

Solargard Rust Primer WB is a water-based, acrylic, metal primer formulated to protect metal substrates against atmospheric corrosion.

BASIC USES

Solargard Rust Primer WB is used on metal substrates in conjunction with Tremco Roofing's Solargard 6083, Acrythane, Hy-Build, Acrylic Sealer and Seam Sealer products.

PACKAGING

5 gal (18.9 L) pail

COLOR

Milky White

GRADE

Brush, Roller, Spray

STORAGE

12 months shelf life in unopened containers when properly stored.

DO NOT FREEZE

Recommended storage is indoors in a ventilated, dry area removed from heat, open flame, ignition sources, and direct sunlight. Storage temperatures should range from 60-70°F (15-21°C) and must not drop below 32°F (0°C) or exceed 110°F (43°C).

On the job site, materials should remain on the pallet until use and be stored in a shaded, ventilated area. Materials should be covered with a light-colored, reflective tarp for protection against the elements. Allow for adequate air flow inside the pallets.

Shelf life could be affected if the product is not stored properly.

APPLICATION

Surface Preparation: Surface must be clean, dry, in sound condition, and free of dirt, debris, and contaminants. Rust must be abraded until it no longer exhibits flaking or chalking. Wet insulation must be identified and replaced. Deficient areas of existing system must be repaired. All repairs should be made with like materials matching the existing components and allowed to properly cure prior to application of liquid-applied products.

If the surface has a pre-existing coating, paint or sealant, please contact Tremco for adhesion/compatibility testing and surface preparation recommendations.

Mixing: Use a heavy duty corded power drill with Jiffy Mixer mixing blade. Mix until product is consistent in appearance and viscosity. Do not thin.

Application: Apply to properly prepared surface. Allow primer to dry to support foot traffic before applying Tremco Roofing's approved Solargard liquid applied products. Typical dry time is 1-2 hours. Weather and site conditions may effect the drying process and times.

Solargard® Rust Primer WB

APPLICATION CONTINUED

It is recommended that primed areas are top coated the same day. If primer is exposed overnight, inspect surface prior to application to ensure film is tight and unaffected. If primer has been exposed for more than 72 hours, re-priming is required.

Coverage: 1/2 - 1 gal/100 sq. ft. (8-16 wet mils)

Coverage rates are listed at minimum recommended rates. The application surface can affect the necessary coverage rate.

Additional surface area must be accounted for on applications over corrugated or standing seam metal substrates. Coverage may require an additional 15-25% depending on profile.

Minimum application temperatures must be 50F and rising.

Do not apply when:

- Dew point is within 5°F (2.77°C) of ambient temperatures
- Precipitation, fog, or dew is imminent prior to cure of the product
- Freezing temperatures are expected prior to cure of the product
- Must use heavy-duty or industrial grade spray tips
- Properly clean and maintain spray equipment before, during and after use
- Equipment should be properly grounded during use
- Contact Tremco Roofing Technical Department for detailed spray equipment recommendations

Component	Pressure	Tip Size	Flow Rate	Filters	Hose Type	WHIP	Product Temp
One-Component	1,500 psi	.015 - .025	0.24-.067 gpm	Remove	High Pressure	¼" High Pressure	Ambient

Soap & Water

- Not recommended for use over the following:
Roof Decks: Cementitious wood fiber, metal, poured-in-place gypsum, structural lightweight or lightweight insulating concrete, and wood decks (includes plywood, tongue and groove, etc.).
Products/Systems: Asphalt-based or coal tar gravel surfaced BUR systems, clay tile, expanded or extruded polystyrene insulation, fluoropolymer finished metal, insulation cover boards, polyisocyanurate insulation, shingles, silicone-based products, and tar-based products.
- Not for use under continuous immersion

PROPERTY	TYPICAL VALUE	TEST METHOD
Weight per Gallon	9.9 ± 0.2 lbs.	ASTM D 1475
Solids by Volume	43.9% ± 1%	
Solids by Weight	51.6% ± 1%	
VOC	3 g/L	

Your local Tremco Roofing representative can provide you with effective maintenance procedures, which may vary depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the service of the Tremco Service Staff.

Tremco is a US Registered trademark of Tremco CPG Inc.
The information provided on this data page supersedes all previous data concerning this product and its application. The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.

TEMPERATURE RECOMMENDATION

SPRAY EQUIPMENT RECOMMENDATIONS

CLEAN UP

LIMITATIONS

PHYSICAL PROPERTIES

MAINTENANCE

PRECAUTIONS

TECHNICAL SUPPORT



www.tremcoroofing.com
3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

220 Wicksteed Avenue
Toronto, Ontario, M4H 1G7
1.800.668.9879

Tremco Roofing and Building
Maintenance is part of Tremco
Construction Products Group.