

Trisotech[®] Tapered Insulation

Polyisocyanurate Roof Insulation Board

FEATURES

Factory Tapered Insulation

Closed cell foam

Thick fiber facer

FM Approved

UL Approved

BENEFITS

- Provides positive drainage
- Custom layout for rooftops
- High thermal "R-Value"
- Low thermal conductivity
- Non-rotting, non-absorbent core
- Lightweight, rigid board, easy to handle
- Suitable for adhering to substrates in hot or cold applied adhesives
- Protects foam core
- Manufactured under a FM quality assurance inspection program
- Fire/wind protection
- Manufactured under UL quality assurance inspection program
- UL classified fire protection

DESCRIPTION

Trisotech[®] Tapered Insulation consists of a rigid, closed cell polyisocyanurate foam core laminated on both sides to a black, fiber reinforced, non-asphaltic organic felt facer. The board panels are sloped for improved drainage of water. Trisotech Insulation is offered as 20 psi compressive strength as a standard, and a 25 psi compressive strength version is available upon request. Trisotech Tapered Insulation is CFC and HCFC free and the facers are manufactured from 100% recycled material (combination pre-consumer and post-consumer).

BASIC USES

Trisotech Tapered Insulation is used to provide positive drainage of water from rooftop areas. Trisotech Polyisocyanurate boards provide high thermal insulation and are compatible under most roof membrane systems. Trisotech Tapered Insulation Systems include layout drawings to support the design and construction team in providing the best drainage based on the actual conditions of the roof. Tapered Trisotech is recommended for use in combination with a coverboard in hot and cold applied BUR and MB roof systems. Meets ASTM C 1289-11, Type II, Class I, Grade 2 (20 psi) and Grade 3 (25 psi).

SIZES

Trisotech Tapered Insulation is available in truckload quantities in 4' x 4' (1220mm x 1220mm) board panels and packaged on dunnage. Thicknesses range from 1" (25mm) to 4" (101mm). System tapers typically range from 1/8" to 1/2". Contact your Tremco Representative for a full list of available thicknesses.

When Trisotech Tapered Insulation is specified for application in cold adhesive or hot bitumen, the recommended board size is 4' x 4'. Board sizes of 4' x 8' are only acceptable when mechanical attachment of insulation is specified.

APPLICATION

General Application Data: Roof replacement usually involves more complexities than new construction roofing. Often encountered are situations such as rusted/deteriorated decks, rotted wood components, rooftop equipment which cannot be moved or shut down, and numerous other conditions.

The following application information is designed to serve as a general guide. Your local Tremco Representative will prepare detailed specifications based on the condition of your roof.

Structural Decks: Must be properly designed and structurally sound.

Drainage: Ponding conditions are unacceptable and will adversely affect the performance of any roofing system. If positive drainage does not exist, water removal from the roof surface must be facilitated by lowering drains, and/or installing additional drains, tapered insulation, or Tremco approved cellular concrete system.

Insulation Storage: Insulation must be dry and kept dry. When stored outdoors, stack insulation on pallets at least 4 inches (100mm) above ground level. Upon receipt of insulation on the job site, remove the factory plastic packaging. Cover the top and sides of the insulation with waterproof tarpaulin (not polyethylene) and secure. Do not stack more than two pallets high.

Trisotech® Tapered Insulation

APPLICATION CONTINUED

Surface Preparation: Prior to installing the insulation, the substrate must be clean, dry and free of dust, dirt, oil, or other contaminants. Concrete and gypsum decks must be properly cured and sufficiently dry prior to installing insulation.

INSTALLATION

Multiple Layers: The use of two separate layers of insulation is recommended, but required over steel decks. After securing the first layer of insulation, install the additional layer(s) with the board joints offset a minimum 6 inches (150mm) from the joints of the preceding layer. Two layers, with board joints offset, can minimize stress on the roof membrane which results from thermal movement of the deck.

Adhesive Application: Tremco Fas-n-Free, Tremco Low Rise Foam Adhesive, and Tremco Low Rise Foam Adhesive Green are recommended for use with Trisotech Insulation. Obtain and read the Specification Data Sheets for adhesive products prior to use.

Bitumen Application: Hot applied asphalt can be used to adhere Trisotech to concrete decks, to base sheets which are mechanically attached to wood or gypsum decks, and to insulation layer(s) previously secured. Hot asphalt may also be used to adhere coverboards over Trisotech Insulation. Concrete decks should be primed with Tremprime WB and allowed to thoroughly dry. Adhere insulation to substrate in a full coverage of hot applied bitumen, at a coverage rate of 30 lbs. per 100 sq. ft. (1.5 kg/m²) ± 20%. Place insulation immediately into the hot bitumen and step into place to achieve a solid bond.

Mechanical Fastener Application: Tremco Fasteners and Discs are recommended where mechanical attachment of the insulation is specified over steel and wood decks. Do not mix fasteners and discs of different brands unless the combination is Factory Mutual Approved.

Fasteners must be driven perpendicular to the deck. Do not overdrive the fastener, as the insulation may fracture and become susceptible to loss of attachment. Fastener should be driven tight enough so that the disc will not turn.

LIMITATIONS

- Not intended for use under ponding conditions. Positive drainage is required.
- Not to be exposed to solvents, oils or other contaminants harmful to polyisocyanurate foam insulation.
- Insulation stops are required on roofs with slopes of 2:12 (2") or greater.
- Not for use directly under hot applied roof membranes. A wood fiber overlay board is required prior to the application of a hot applied roof membrane.
- Not for use in direct contact with lightweight insulating concrete or recently poured gypsum decks.
- For adhered systems where a cover board is not specified, multiple layers of Trisotech must be used when the total insulation thickness is 3.0" or greater.
- For adhered single ply systems when a cover board is not specified, the maximum thickness for the top layer of Trisotech is 2.7".

PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUE			TEST METHOD
Compressive Strength, min.	Grade 2 - 20 psi (137kPA), Grade 3 - 25 psi (172 kPA)			ASTM D 1621
Density, nominal	2.0 lb/ft ³ (32.0kg/m ³)			ASTM D 1622
Conditioned Thermal Resistance at 75°F (24°C)	R Value			ASTM C 518
	LTTR*	WEIGHT (lbs/sq ft)	RECYCLED CONTENT**	
1" (25.4mm)	5.6	0.167	40%	
2.5" (63.5mm)	14.4	0.417	23%	
3.5" (88.9mm)	20.5	0.583	19%	

* Long Term Thermal Resistance, ASTM C 1289-11

** By weight, combined pre-consumer and post-consumer

Trisotech[®] Tapered Insulation

MAINTENANCE

Your local Tremco Roofing Sales Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

TECHNICAL SUPPORT

Your local Tremco Roofing Sales Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



Roofing & Building Maintenance

www.tremcoroofing.com

3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

50 Beth Nealson Drive
Toronto, Ontario M4H 1M6
1.800.668.9879

Tremco Roofing & Building
Maintenance is a part of the Tremco
Construction Products Group

Tremco is a US Registered trademark of Tremco Incorporated.

The information provided on this data page supersedes all previous data concerning this product and its application.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.