

## Polyester fabric

<b>DESCRIPTION:</b>	PERMAFAB is 100% stitchbonded, polyester fabric that offers an unusual combination of high strength properties with good elongation for excellent resistance against thermal stress. PERMAFAB polyester fabric will not rot as it ages and it is resistant to moisture.																						
<b>BASIC USES:</b>	PERMAFAB is designed to be used in conjunction with ALPHAGUARD, ICE Coating, SOLARGARD 6083, and GEOGARD coatings as a maintenance overlayment for smooth surfaces, and single ply roofs. PERMAFAB is also used in conjunction with SOLARGARD Acrylic Sealer, SOLARGARD Seam Sealer and GEOGARD Seam Sealer for flashing, seam, penetration, and other detail repairs.																						
<b>PACKAGING:</b>	#230004R – 4" x 300' roll (101.6 mm x 7.62 m) #230006R – 6" x 300' roll (152.4 mm x 7.62 m) #230012R – 12" x 300' roll (304.8 mm x 7.62 m) #290400 – 40" x 324' roll (1016 mm x 8.23 m)																						
<b>COVERAGE RATE:</b>	<b>One roll of PERMAFAB will cover:</b> 40" ↔ 324' (1016 mm ↔ 8.23 m) 1,101 sq. ft. (gross), 11.0 squares (102.3 m <sup>2</sup> ) <b>A single overlayment with:</b> 4" (101.6 mm) overlap 972 sq. ft. (net), 9.7 squares (90.3 m <sup>2</sup> )																						
<b>APPLICATION:</b>	Refer to the following Product Data Sheets and/or substrate specific general guideline specifications for complete application information: ALPHAGUARD, GEOGARD, ICE Coating, SOLARGARD 6083, SOLARGARD Acrylic Sealer, SOLARGARD Seam Sealer and GEOGARD Seam Sealer.																						
<b>LIMITATIONS:</b>	<ul style="list-style-type: none"> <li>• Application temperature shall be above 40°F (4.4°C).</li> <li>• Do not apply when rain is imminent.</li> <li>• Not to be directly embedded into or coated with any ALUMANATION coatings.</li> </ul>																						
<b>TECHNICAL DATA:</b>	<table border="0"> <tr> <td>Weight per Sq. Yd (m<sup>2</sup>)</td> <td>3 oz. (0.1 kg)</td> </tr> <tr> <td>Weight per Roll</td> <td>33 lbs. (13.6 kg)/40" roll (8.23m)</td> </tr> </table> <table border="0"> <thead> <tr> <th>Property</th> <th>Test Method</th> <th>Typical Value</th> </tr> </thead> <tbody> <tr> <td>Elongation</td> <td>ASTM D 1682</td> <td>61.65% avg.*</td> </tr> <tr> <td>Tensile</td> <td>ASTM D 1682</td> <td>51.1 lbs. (23.2 kg) avg.*</td> </tr> <tr> <td>Mullen Burst</td> <td>ASTM D 3786</td> <td>176.8 lbs. (80.2 kg)</td> </tr> <tr> <td>Trapezoid (Tear Strength)</td> <td>ASTM D 1117</td> <td>16.1 lbs. (7.3 kg) avg.*</td> </tr> <tr> <td>Mildew &amp; Rot Resistance</td> <td></td> <td>Excellent</td> </tr> </tbody> </table> <p><i>*NOTE: Average machine &amp; cross machine direction.</i></p>	Weight per Sq. Yd (m <sup>2</sup> )	3 oz. (0.1 kg)	Weight per Roll	33 lbs. (13.6 kg)/40" roll (8.23m)	Property	Test Method	Typical Value	Elongation	ASTM D 1682	61.65% avg.*	Tensile	ASTM D 1682	51.1 lbs. (23.2 kg) avg.*	Mullen Burst	ASTM D 3786	176.8 lbs. (80.2 kg)	Trapezoid (Tear Strength)	ASTM D 1117	16.1 lbs. (7.3 kg) avg.*	Mildew & Rot Resistance		Excellent
Weight per Sq. Yd (m <sup>2</sup> )	3 oz. (0.1 kg)																						
Weight per Roll	33 lbs. (13.6 kg)/40" roll (8.23m)																						
Property	Test Method	Typical Value																					
Elongation	ASTM D 1682	61.65% avg.*																					
Tensile	ASTM D 1682	51.1 lbs. (23.2 kg) avg.*																					
Mullen Burst	ASTM D 3786	176.8 lbs. (80.2 kg)																					
Trapezoid (Tear Strength)	ASTM D 1117	16.1 lbs. (7.3 kg) avg.*																					
Mildew & Rot Resistance		Excellent																					
<b>MAINTENANCE:</b>	Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.																						

### TECHNICAL SERVICES:

Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the services of the Tremco Technical Service Staff.

# PERMAFAB



D-290  
7/31/18

**www.tremcoroofing.com**  
3735 Green Road  
Beachwood, Ohio 44122  
1.800.852.6013  
  
50 Beth Nealson Drive  
Toronto, Ontario M4H 1M6  
1.800.668.9879

PERMAFAB is a U.S. registered trademark of Tremco Incorporated.

The information provided on this data sheet is effective as of July 2018 and supersedes all previous data concerning this product and its application.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCES SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.