

SOLARGARD® HY-BUILD

#1512-53 – 53 gallon drum

#1512-05 – 5 gallon pail

#1512-01 – 1 gallon cans

Elastomeric roof and wall coating

Description

SOLARGARD HY-BUILD is a water-based, acrylic, elastomeric roof and wall coating formulated to provide a tough, durable, flexible, breathable film protection of metal roofs and previously painted or unpainted masonry walls.

Uses

SOLARGARD HY-BUILD waterproofs metal roofs as well as masonry, stucco, EIFS and metal wall surfaces.

Advantages

SOLARGARD HY-BUILD's formulation resists the effects of water and weather making it an ideal coating for long-lasting waterproofing protection. In addition, SOLARGARD HY-BUILD contains fibers, which allow it to protect against abrasion and building movement. It will bridge small cracks.

Limitations

Application temperature shall be above 50°F. Protect from freezing. Not intended for use in areas subject to vehicular traffic or where water continuously ponds. Do not apply when rain is imminent. Do not apply over silicone or coal tar.

Preparation

All surfaces are to be free of dirt, grease, oil, loose paint, loose rust, excess chalk, and other foreign matter which could prevent proper adhesion. This is best accomplished using a high-pressure power wash of at least 2,000 psi. A surface cleaner shall be used to remove all grease or oily deposits.

TECHNICAL DATA

Weight per Gallon (ASTM D 1475) 11.0 ± 0.2 lbs.

Specific Gravity (ASTM D 1475) 1.32 ± 0.2

Solids by Weight (ASTM D- 1353) 63% ± 1%

Solids by Volume (ASTM D 5201) 52% ± 1%

Elongation @ 77°F (ASTM D 2370) 215% ± 25%

Flexibility @ -15°F (ASTM D 522) Passes 1/2 inch mandrel bend

Tensile Strength @ 77°F 375 ± 50 psi

Tear Resistance (ASTM D 522) 138 lbf/in

(ASTM D 2370)

Dry Time (ASTM D 1640) 1 hour to touch

Flashpoint (ASTM D 3278) None

Permeance Rating 12

Clean Up Soap and water

COVERAGE

Porosity, texture of surface, and specified dry-film thickness will dictate coverage. Coverage rates are as follows:

Walls 1 1/2 gal./100 sq. ft. 24 wet mils

Metal Roofs 2 gal./100 sq. ft. 32 wet mils

If metal panel finish is Kynar 500 or the roof/wall was previously coated, please contact the Republic Technical Department for surface preparation recommendations.

Application

Refer to application specifications for additional information.

Walls: Over porous concrete, brick, etc., surfaces where a prime coat is recommended use SOLARGARD MASONRY PRIMER. SOLARGARD HY-BUILD can be applied by brush, roller, or spray gun to specified coverage rates.

Refer to appropriate application specification for further information.

Metal: Prime all rust using SOLARGARD RUST PRIMER WB. SOLARGARD HY-BUILD can be applied by brush, roller or spray gun to specified coverage rates.

Refer to appropriate application specification for further information.

Spray Equipment Recommendation

Pumps: Graco King 45:1, Graco Bulldog 30:1 or gas powered equivalents. Graco GH733, HydraMax 350 or GMax 7900 or other manufacturers' equivalents.

Hose/Pressure: 50 –300 length (depending on spray rig pressure). When using hoses longer than 100 use the next larger hose ID every 50 . Every 50 of hose will reduce the spray pressure of the rig by 10% at the gun tip. i.e. 300 hose – 3/4" (50/100) to 5/8" (50/100) to 1/2" (50/100) to 3/8" (50')

Tip Sizes:

Fan Width (in)	.039	.041	.043	.045	.047	.049
10"–12"	539	541	543	545	547	549
12"–14"	639	641	643	645	647	649
14"–16"	739	741	743		747	749
16"–18"	839	841	843		847	
Flow Rate	1.60 gpm	1.80 gpm	1.98 gpm	2.17 gpm	2.37 gpm	2.58 gpm

Good results are generally obtained @ 2000–3000 psi at spray tip.

Gun: Graco Contractor Gun, Graco Contractor FTx gun, Graco Silver Plus or equivalent. (Tip extrusions or pole guns can be used.)



REPUBLIC
RESTORATION SYSTEMS

TREMCO

SOLARGARD® HY-BUILD

For additional information, refer to appropriate application specification.

Maintenance

It is recommended that the coating application be checked on a regular schedule with additional inspections after the system has been exposed to severe conditions. Recoating or small area touch up can be made at any time by following recommended application procedures.

Technical Services

Technical advice or service on suitability of material for specific application and end-use requirements is available from the manufacturer. Refer to label and Material Safety Data Sheet (MSDS) for precautionary information.



Tremco Incorporated
3735 Green Road, Beachwood, OH 44122
U.S.: 800-551-7081
50 Beth Neelson Drive, Toronto, Ontario M4H 1M6
CA: 800-668-9879
www.tremcoroofing.com

SOLARGARD is a U.S. registered trademark of Republic Powdered Metals, Inc.

The information provided on this data sheet is effective as of February 2016 and supersedes all previous data concerning this product and its application.

© Republic Restoration Systems by Tremco, 2016. All Rights Reserved.

The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCES SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.