

TremPly® Max TPO Single Ply Roofing Systems

Environmentally Friendly, Long-Lasting Single Ply Adhered Roofing System

FEATURES

Great Value

Excellent Seam Strength

Long-term Weathering

Energy Saving

Inherently Flexible

Fungal Resistant

BENEFITS

• Excellent performance at a cost-effective price.


• Heat-welded seams provide greater seam strength to taped and other seams.

• Excellent long-term heat and UV resistance.

• Highly reflective and emissive white surface can help reduce energy use and urban heat island effect.

• No need for plasticizers.

• Doesn't require biocides.



DESCRIPTION

TremPly® Max TPO Single Ply Roofing System is a smooth back thermoplastic roofing membrane. It is offered in 5-foot and 10-foot-wide sheets that feature heat welded seam integrity and overall exceptional value. The TremPly MAX TPO material has been formulated for maximum weatherability and exceeds the ASTM heat aging requirement by 4 times.

BASIC USES

TremPly Max TPO is offered white, gray and tan colors with 50 mil, 60 mil, 70 mil and 80 mil thickness. TremPly Max TPO is also available in a fleece back version which is detailed on a separate data sheet. They are excellent choices for roof overlays, replacement and new construction alike. Tremco also offers TremPly TPO as a more economical alternative to the TremPly Max TPO.

COLOR

White

GRADE

TremPly Max TPO is offered in 50mil, 60mil, 70mil and 80mil thicknesses. TremPly TPO and Fleeceback versions are available and detailed on separate data sheets.

STORAGE LIFE

Store rolls on their sides on pallets or shelving in a dry area. Jobsite specific be sure to cover or tarp when not in use.

COVERAGE RATE

Available in 10'x100' (1,000 sq. ft.) and 5'x100' sheets (500 sq. ft.)

APPLICATIONS

TremPly Max TPO is available as a mechanically attached, fully adhered, ballasted, or a heat induction welded systems. Field seaming is accomplished by fusing the thermoplastic membrane with conventional hot air welding equipment. It comes with a full line of readily available, pre-fabricated accessories designed to save time and money. TremPly Max TPO Roofing Systems carry extensive FM Global and Underwriters Laboratories' approvals.

Please refer to Tremco application guides and project specific specifications or consult with your local Tremco Roofing sales representative for project specific application requirements.

LIMITATIONS

Follow recommendations for applicable adhesives or installation methods in low temperature situations.



TremPly® Max TPO Single Ply Roofing Systems

PHYSICAL PROPERTIES

PROPERTY	ASTM D6878 MINIMUM	TPO 50 MIL	TPO 60 MIL	TPO 70 MIL	TPO 80 MIL
Normal Thickness ASTM D751	0.039" (min.) (0.99 mm)	0.050" (1.27 mm)	0.060" (1.52 mm)	0.070" (1.78 mm)	0.080" (2.03 mm)
Breaking Strength ASTM D751 Grab Method	220 lbf/in. (38.5 kn/m)	305 lbf x 290 lbf (454 x 432.1 kg/m)	305 lbf x 290 lbf (454 x 432 kg/m)	335 lbf x 320 lbf (499 x 477 kg/m)	335 lbf x 320 lbf (499 x 477 kg/m)
Factory Seam Strength ASTM D751	66 lbf (98.34 kg/m)	150 lbf (223.5 kg/m) (membrane failure)	150 lbf (223.5 kg/m) (membrane failure)	165 lbf (456 kg/m) (membrane failure)	165 lbf (456 kg/m) (membrane failure)
Elongation at break ASTM D751	15%	30%	30%	30%	30%
Heat Aging ASTM D751	90% retention of Breaking Strength & Elongation at break	100%	100%	100%	100%
Tear Strength ASTM D751 8" x 8" (203 x 203 mm) Sample	55 lbf (81.95 kg/m)	70 lbf x 110 lbf (104.3 x 163.9 kg/m)	65 lbf x 130 lbf (96.85 x 193.7 kg/m)	60 lbf x 150 lbf (89.4 x 223.5 kg/m)	60 lbf x 150 lbf (89.4 x 223.5 kg/m)
Puncture Resistance FTM 101C Method 2031	Not Established	380 (172 kg)	380 (172 kg)	380 (172 kg)	380 (172 kg)
Cold Brittleness ASTM D2137	(-40°C)	-40° C	-40° C	-40° C	-40° C
Permeance ASTM E96	Not Established	0.08 Perms	0.08 Perms	0.08 Perms	0.08 Perms
Dimensional Change ASTM D1204 @ 158°F (70°C), 6 hrs.	(+/-1%)	0.40%	0.40%	0.40%	0.40%
Water Absorption ASTM D471 @ 158°F (70°C), 1 week	(+/-3.0%)	0.70%	0.70%	0.70%	0.70%
Hydrostatic Resistance ASTM D751 Method D	Not Established	430 psi	430 psi	430 psi	430 psi
Ozone Resistance ASTM 1149	No visible deterioration @ 7x magnification	No visible deterioration @ 7x magnification	No visible deterioration @ 7x magnification	No visible deterioration @ 7x magnification	No visible deterioration @ 7x magnification
Reflectivity (white) initial/aged ASTM C1549, ASTM E903	N/A	0.835/0.72	0.835/0.73	0.835/0.72	0.835/0.72
Emissivity (white) Initial/aged ASTM C1371, ASTM E403	N/A	0.84/0.91	0.84/0.91	0.84/0.91	0.84/0.91
Weather Resistance ASTM G155 /D6878	10,080 KJ/(m ² x nm) at 340 nm	>46,000 KJ/(m ² . nm) at 340 nm	>46,000 KJ/(m ² . nm) at 340 nm	>46,000 KJ/(m ² . nm) at 340 nm	>46,000 KJ/(m ² . nm) at 340 nm
Heat Aging ASTM D573	240°F (115°C) for 32 weeks	128 weeks	128 weeks	128 weeks	128 weeks
Thickness Above Scrim ASTM D7635	Min 30% of Total Thickness	17.9 mil (Nominal)	21.5 mil (Nominal)	25.7 mil (Nominal)	31.5 mil (Nominal)

Note: This data based on typical product performance for each thickness of membrane, and are subject to normal manufacturing tolerances and variances. Certain data are provided in MD (machine direction) x CMD (cross machine direction) format. Visit www.tremcoroofing.com for latest data. **Important Note:** Tremco TPO membranes meet and/or exceed ASTM D-6878 standards for thermoplastic TPO membranes.

MAINTENANCE

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

TECHNICAL SUPPORT

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



www.tremcoroofing.com
3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

50 Beth Nealson Drive
Toronto, Ontario M4H 1M6
1.800.668.9879

Tremco is a US Registered trademark of Tremco Incorporated.

The information provided on this data page supersedes all previous data concerning this product and its application. The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury to person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.