Tremfix[®]

A Tar-Based Roof Cement for Low Slope Roofing and Roof Repairs

FEATURES

BENEFITS

Adheres to wet surfaces

Trowel

Emergency repairs can be made immediately Minimizes water damage

Easily troweled

• Can be used on rough surfaces

DESCRIPTION

Tremfix is asbestos free. Tremfix meets ASTM D5643, the Standard Specification for Asbestos Free Coal Tar Roof Cement.

BASIC USES

PACKAGING

Tremfix is used for general repairs on coal-tar roofs, including breaks and blisters. Tremfix can be used effectively for emergency repairs on wet roof surfaces of both asphalt and coal-tar BUR. Added strength can be obtained by using reinforcing membranes.

Tremfix* is composed of coal-tar pitch, reinforcing fibers, and plasticizers blended for year-round roof repair.

Tremfix is available in 3 gallon (11.3L) containers.

• Not intended for vertical surfaces or pronounced slopes.

• Not for use on EPDM, PVC, TPO, or PIB single ply roof membranes.

GRADE STORAGE LIFE

COVERAGE

APPLICATION

Up to one year in unopened container.

PROPERTY

Asbestos content

Viscosity @ 77 °F (25° C)

Density @ 77°F (25° C)

Nonvolatile matter, min

Behavior at 140°F (sag resistance)

(less water, less exempt solvent)

Adhesion to wet surface, min

Volatile organic compound

Remove loose gravel, dirt, dust, rotted felt, and foreign matter. Apply over clean, sound, dry base for permanent repairs. Temporary emergency repairs can be applied over wet surfaces.

12 gal/100 ft² (4.8 L/m²) in a single troweled layer at approximately 1/8" (3 mm) thickness, or 25 ft²/5 gallon pail in a 3 course (mastic, reinforcement, mastic) application. Rates will vary depending on ambient temperature and actual surface conditions.

TYPICAL VALUE

9.1 lb/gal (1.09 kg/L)

1/8 inch (3 mm) max

None

73%

75%

<300 g/l

TEST METHOD

ASTM D 2196

ASTM D 1475

ASTM D 4022

ASTM D 4586

ASTM D 3409

ASTM D 3960

EPA 600/R-93/116

LIMITATIONS

PHYSICAL PROPERTIES

MAINTENANCE

PRECAUTIONS

Your local Tremco Roofing Sales Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

480,000-1,000,000 cP (480-1,000 Pa•s)

TECHNICAL SUPPORT

Tremfix[®]

Your local Tremco Roofing Sales Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



Roofing & Building Maintenance

www.tremcoroofing.com 3735 Green Road Beachwood, Ohio 44122 1.800.852.6013

50 Beth Nealson Drive Toronto, Ontario M4H 1M6 1.800.668.9879

Tremco Roofing & Building Maintenance is a part of the Tremco Construction Products Group

Tremco is a US Registered trademark of Tremco Incorporated. The information provided on this data page supersedes all previous data concerning this product and its application. The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Temco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY, IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.