

# Uncured Flashing

## Self-Adhering Flashing

**Composition:** Tremco Uncured Flashing is a uncured 0.045" EPDM membrane laminated to a 0.025" black butyl-base pressure-sensitive fully cured adhesive/sealant for single ply roofing membranes.

**Basic Uses:** Tremco Uncured Flashing may be used for general purpose flashing of roof top protrusions, patching, and repairing seams. Tremco Uncured Flashing was specifically developed for use with EPDM single ply membrane. However, it adheres well to most types of single ply roofing membranes.

**Limitations:**

- Do not remove roll from container until installation
- Do not apply to wet surfaces
- Do not use over asphalt mastics or previously applied adhesives.

**Packaging:** Available rolls 6"x100' 2-rolls/box, 9", 12" x 100' 1-roll/box

**Storage Life:** The uncured flashing will continue to cure overtime. When stored indoors, out of direct sunlight, and in original unopened container between 60° F (15° C) and 80° F (26.6° C) the shelf life is 6 MONTHS

| Product Advantages                             |                                 |
|--|---------------------------------|
| Features                                       | Benefits                        |
| Easy, Fast Application                         | • Reduces Labor Cost            |
| 100% Solids                                    | • No Volatile Organic Compounds |
| Excellent heat, water, and chemical resistance | • Long performance life         |

**Surface Preparation:** Surface must be clean, dry, free of dirt, oil, debris, dust, and other contaminants.

**Application:** Prime the area to be flashed with Tremco Primer/Splice Wash. When primer/splice wash is dry, align the roll of membrane adjacent to the area to be flashed. Unroll the membrane, cut to the desired length and trim the corners of the membrane to ensure that they are rounded. Remove the release paper. Cup the flashing slightly. Adhere the center portion of the membrane first, and position the balance of the membrane by applying firm hand pressure. DO NOT STRETCH MATERIAL. Roll the membrane with a hand roller to insure a water-tight seal.

**Coverage:**

6" X 100' approximately 50 sq.ft./roll  
9" x 100' approximately 75 sq.ft./roll  
12" x 100' approximately 100 sq.ft./roll

**Precautions:** Users must read container labels and Material Safety Data Sheets for health and safety precautions prior to use.

**Availability and Cost:** Contact your local Tremco Roofing Representative for pricing and availability. For the name and number of your Representative, call the Roofing Division at 216/292-5000.

**Maintenance:** Your local Tremco Roofing Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventive maintenance are all part of a sound roof program.

**TREMCO**

Roofing & Weatherproofing Peace of Mind™

**Guarantee/Warranty:** Tremco Inc. warrants Uncured Flashing to be free of defects and to meet published physical properties when tested according to ASTM and Tremco standards. Under this warranty, any Uncured Flashing product that is proved to be defective when applied in accordance to our written instructions, and in applications recommended by Tremco as suitable for this product will be replaced with like product at no charge. **THIS IS BUYERS SOLE AND EXCLUSIVE REMEDY.**

All claims concerning product defects must be made in writing within twelve (12) months of shipment. The absence of such claims in writing during this period will constitute a waiver of all claims with respect to such product. This warranty shall be IN LIEU OF any other warranty, express or implied, including but not limited to, any implied warranty of MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.

**Technical Services:** Your local Tremco Representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications. The services of the Tremco Research Center, which has earned a unique reputation in weatherproofing technology, complement and extend the services of the Tremco Technical Service staff.

**Statement of Policy and Responsibility:** Tremco takes responsibility for furnishing quality materials and for providing specifications and recommendations for their proper installation.

As neither Tremco itself nor its Representatives practice architecture or engineering, Tremco offers no opinion on, and expressly disclaims any responsibility for the soundness of any structure on which its products may be applied. If questions arise as to the soundness of a structure or its ability to support a planned installation properly, the Owner should obtain the opinion of competent structural engineers before proceeding. Tremco accepts no liability for any structural failure or for resultant damages, and no Tremco Representative is authorized to vary this disclaimer.

| <b>Physical Performance Characteristics</b> |                                    |                    |
|---|------------------------------------|--------------------|
| <b>Uncured Flashing Adhesive/Sealant</b>    |                                    |                    |
| <b>Property</b>                             | <b>Typical Value</b>               | <b>Test Method</b> |
| Tensile                                     | 100 psi                            | ASTM 412           |
| Elongation                                  | 1,200%                             | ASTM 412           |
| Heat Aging at 300°F                         | No appearance change after 180 hrs | ASTM 412           |
| Brittleness Temperature °F                  | Less than -50                      | ASTM 412           |



3735 Green Road  
Beachwood, OH 44122  
216-292-5000

220 Wicksteed Ave  
Toronto, ONT M4H 1G7  
416-421-3300