

POWERply Cold 360

A Cold Applied, Seamless, Modified Bitumen Roof System

FEATURES

Cold applied
Low odour
Polymer modified plies
Seamless
Polyester reinforcement

BENEFITS

- No flames, hot kettles or smoke
- Can be readily used in odour-sensitive areas such as schools and health care facilities
- Membrane flexibility to resist thermal shock and splitting
- Continuous waterproofing protection without exposed lap edges
- Strong and pliable to resist punctures, tears and splits

DESCRIPTION

The POWERply Cold 360 Modified Bitumen Roof System consists of two smooth surfaced, polyester reinforced SBS modified bitumen plies adhered and floodcoated with POWERply Standard Cold Adhesive, a unique, cold process, modified asphalt based adhesive. The system is then finished with a gravel surfacing. The system combines the flexibility of polymer modified membrane and a cold applied adhesive with the seamless and multi-ply assembly of a time tested built-up roof.

BASIC USES

POWERply Cold 360 can be used as a new or replacement membrane wherever a premium modified bitumen or built-up roof system is appropriate, but where it is desired to have a low odour roof system or a roof system suitable for use in areas with difficult access.

LIMITATIONS

- Do not install directly over wet Insulation or substrates
- Do not install directly over any foam insulation

PACKAGING

POWERply Standard Cold Adhesive is available in 18.9L (5 Gal) and 200 L (53 Gal) containers. Estimate coverage of smooth modified bitumen at approximately 147 sqft/roll/ply.

GENERAL APPLICATION DATA

Roof replacement usually involves more complexities than new construction roofing. Often encountered are situations such as rusted/deteriorated decks, rotted wood components, rooftop equipment which cannot be moved or shut down, and numerous other conditions.

The following application information is designed to serve as a general guide. Your local Tremco Representative will prepare detailed specifications based on the condition of your roof.

STRUCTURAL DECKS

Must be properly designed and structurally sound to support and secure the POWERply Cold 360 roof system.

VAPOUR/AIR BARRIER

Vapour/Air Barrier: Where specified, ensure proper design and installation.

DRAINAGE

Excessive ponding conditions can adversely affect the performance of any roof system. Where positive drainage does not exist, water removal from the roof surface must be facilitated by lowering sumps, installing tapered insulation or additional drains.

INSTALLATION

Insulation must be dry and kept dry. No more insulation shall be installed than can be covered that day. Insulation may be secured with mechanical fasteners or a Tremco approved hot or cold applied adhesive as specified. Asphalt coated fibreboard is the recommended overlay board.

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

POWERply Cold 360

INSTALLATION PROCEDURES

According to particular job specifications, prepare surface to be covered:

- Replace areas of wet insulation, deteriorated deck and wood components.
- Install roof insulation or nailed base sheet.

1. Prior to placement, cut modified bitumen in 16' to 20' lengths. Allow lengths to relax at least 30 minutes at 13°C (55°F) or above. Allow approximately 60 minutes to relax at temperatures below 13°C (55°F).
2. Starting at the low point of the roof, install 2 plies of smooth modified bitumen. Place to ensure that water will flow over or parallel to, but not against exposed edges. Lap ends 150 mm (6 in) and stagger all laps 300mm (12 in), minimum. Dry roll each ply to ensure proper alignment, prior to adhering with POWERply Standard Cold Adhesive.
3. Immediately embed each ply in uniform applications of POWERply Standard Cold Adhesive, spray or brush applied at approximately 0.8 litres/sqm (2 gal/sq) per ply.
4. Install flashings incorporating either Elastomeric Sheeting or 2 plies of Modified Bitumen as specified.

SURFACING

Apply POWERply Standard Cold Adhesive at 2.4 litres/sqm (6 gal/sq) and immediately broadcast 20 kg/sqm (400 lb/sq) of new, clean pea gravel.

AVAILABILITY/COST

Immediately available from Tremco at strategic locations throughout Canada. Cost data is available from your local Tremco Representative. For name and number of your local Tremco Representative, call 416/421-1300 in Canada or 800/263-6046. In the U.S. call 216/292-5000 or 800/852-6013.

GUARANTEE/WARRANTY

We warrant our products to be free from defects and manufactured to meet published physical properties when cured and tested according to ASTM, CSA and Tremco standards. Under this warranty, we will provide, at no charge, additional product to replace any product proved to be defective when applied in accordance with our written instructions and in applications recommended by us as suitable for this product.

All claims concerning product defect must be made within twelve (12) months of shipment. Absence of such claims in writing during this period will constitute a waiver of all claims with respect to such product. This warranty is in lieu of any and all other warranties expressed or implied.

MAINTENANCE

Your local Tremco Roofing sales representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

TECHNICAL SUPPORT

Your local Tremco Roofing sales representative, working with the Technical Service Staff, can help analyze conditions and needs to develop recommendations for special applications.



Roofing & Building Maintenance

www.tremcoroofing.com
3735 Green Road
Beachwood, Ohio 44122
1.800.852.6013

220 Wicksteed Avenue
Toronto, Ontario M3H 1G7
1.800.668.9879

Tremco Roofing and Building
Maintenance is part of Tremco
Construction Products Group

Tremco is a US Registered trademark of Tremco CPG Inc.

The information provided on this data page supersedes all previous data concerning this product and its application. The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.