

# POWERply® Standard FR GT24C

*A Highly Reflective,  
Granule Surfaced  
Modified Bitumen Membrane*



## DESCRIPTION

POWERply® Standard FR GT24C is a fire rated, fiberglass reinforced, SBS modified bitumen membrane. This membrane is manufactured with ultra white granule layer which provides a highly reflective surfacing. POWERply Standard FR GT24C is also asbestos free. POWERply Standard FR GT24C exceeds ASTM D 6163, Type I, Grade G.

## BASIC USES

POWERply Standard FR GT24C is designed for application in both hot and cold applied roof systems where a granule surfaced membrane is desired. POWERply Standard FR GT24C is a component of many hot and cold applied Class A fire rated roof systems. Refer to UL Roofing Materials and Systems Directory for applicable system configurations. POWERply Standard FR GT24C exceeds the minimum requirements for aged solar reflectance per the 2015 International Energy Conservation Code (Chapter 4, Section C402.3.1).

## DIMENSIONS

POWERply Standard FR GT24C is a 140 mil (3.56 mm) thick membrane with a 3" (76 mm) selvedge. Roll covers 97.5 sq ft (9.05 m<sup>2</sup>) when applied, with roll dimensions of 39-3/8" x 32'8" (1 m x 9.95m). Approximate roll weight is 98 lbs (44.4 kg). Available in pallets only, with 23 rolls per pallet.

## APPLICATION

**General Application Data:** The following application information is designed to serve as a general guide. Your local Tremco Representative will prepare detailed specifications based upon your roof's conditions.

**Drainage:** Ponding conditions are unacceptable and will adversely affect performance of any roofing system. If positive drainage does not exist, water removal must be facilitated by lowering drains, and/or installing additional drains, tapered insulation, or a Tremco approved lightweight cellular insulating concrete slope system.

**Insulation:** Insulation must be dry and kept dry. No more insulation shall be installed than can be covered that day.

**Installation Procedures:** According to job specifications, prepare the surface to be covered:

- Replace areas of wet insulation, deteriorated deck and wood components.
- Install roof insulation or nailed base sheet and multi-ply base ply system.

**Cold Process POWERply Standard FR GT24C:** For application in cold process adhesive, cut POWERply Standard FR GT24C in 16 to 18' (4.9-5.5 m) lengths maximum. Allow lengths to relax. Above 55°F (13°C): 60 minutes minimum. Below 55°F (13°C): 120 minutes minimum.

**Hot Applied POWERply Standard FR GT24C:** THERMastic 100, THERMastic 80, and Premium IV Asphalt are recommended as adhesives for POWERply Standard FR GT24C. Hot applied modified bitumen membranes require special application techniques under cool ambient temperatures and/or moderate wind conditions. Consult your local Tremco Representative for specific recommendations.

**Application:** Plan the placement of POWERply Standard FR GT24C to ensure that water flows over or along, but not against, the exposed edges.

Starting at the low point of the roof, apply a uniform and continuous application of adhesive according to specifications. Embed ply sheets as specified. Avoid walking on plies during placement.

# POWERply® Standard FR GT24C

## APPLICATION CONTINUED

Place POWERply Standard FR GT24C in a uniform and continuous application of adhesive. For cold process applications, press the membrane into the adhesive using a minimum 75 pound weighted roller to assure full contact of the back of the membrane into the adhesive. Lap selvage 3" (76 mm) minimum; end laps 6" (150mm) minimum. Offset laps from base laps. Stagger ends 36" (1 m) minimum. Side laps and end laps may be adhered using hot or cold applied methods. Electric hot air heat welding equipment with a 3" air nozzle is the preferred method for adhering lap areas. However, hot bitumen and cold adhesives may be used. To assure complete and uniform adhesion, adhesive should exude slightly past lap edges.


## LIMITATIONS

- Not intended to perform under ponding conditions. Positive drainage required.
- Not to be exposed to solvents, oils, or other contaminants harmful to asphaltic materials.
- Backnail on roofs with slopes 2:12 (2" per foot) (16.6%) or greater.

## PHYSICAL PROPERTIES

PROPERTY	TYPICAL VALUE		TEST METHOD
Thickness	0.140 in. (3.56 mm)		ASTM D5147
Tensile strength @ 0°F (-18°C)	120 lbf/in. MD (21kN/m), 80 lbf/in XMD (14kN/m)		ASTM D5147
Elongation at 0°F (-18°C)	4% MD, 4% XMD		ASTM D5147
Tensile Strength @ 77°F (25°C)	70 lbf/in MD (12.3kN/m), 35 lbf/in XMD 6.15 kN/m		ASTM D5147
Elongation at 77°F (25°C)	4% MD, 4% XMD		ASTM D5147
Tear strength at 77°F (25°C)	100 lbf MD (445N), 80 lbf XMD (356 N)		ASTM D5147
Low Temp Flex	0° F (-17.7°C)		ASTM D5147
Dimensional Stability	pass		ASTM D5147
Compound Stability @ 215°F (102°C)	pass		ASTM D5147
	INITIAL	AGED*	
Solar Reflectance	0.72	0.63	ASTM C1549
Thermal Emittance	0.91	0.91	ASTM C1371
SRI	88	77	ASTM E1980

\*Aged per ASTM D7987 and CRRC-1



**Rated Product ID #: 0612-0374**

	Initial	Aged
<b>Solar Reflectance</b>	<b>0.72</b>	<b>0.63*</b>
<b>Thermal Emittance</b>	<b>0.91</b>	<b>0.91*</b>

The ratings above are subject to CRRC rating program conditions, requirements, and limitations. Visit [coolroofs.org](http://coolroofs.org) for important information and disclaimers about CRRC rating conditions, requirements, and limitations.

**RAPID RATINGS**  
\*CRRC Rapid Ratings: Interim laboratory-aged values that simulate naturally-aged values and will be replaced by the measured three-year naturally-aged values upon completion of the weathering process.

## MAINTENANCE

Your local Tremco Roofing Sales Representative can provide you with effective maintenance procedures which may vary, depending upon specific conditions. Periodic inspections, early repairs and preventative maintenance are all part of a sound roof program.

## PRECAUTIONS

Users must read container labels and Safety Data Sheets for health and safety precautions prior to use.

## TECHNICAL SUPPORT

Your local Tremco Roofing Sales Representative, working with the Technical Service staff, can help analyze conditions and needs to develop recommendations for special applications.



Roofing & Building Maintenance

3735 Green Road  
Beachwood, Ohio 44122

220 Wicksteed Avenue  
Toronto, Ontario, M4H 1G7

[www.tremcoroofing.com](http://www.tremcoroofing.com)

1.800.852.6013

Tremco Roofing and Building Maintenance is part of Tremco Construction Products Group.

Tremco is a US Registered trademark of Tremco CPG Inc.

The information provided on this data page supersedes all previous data concerning this product and its application. The Statements provided concerning the materials shown are intended solely as a general guide for material usage and are believed to be true and accurate. Since the manner of use is beyond our control, Tremco DOES NOT MAKE NOR DOES IT AUTHORIZE ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PURPOSE, OR ANY OTHER WARRANTY, GUARANTEE OR REPRESENTATION, EXPRESSED OR IMPLIED, CONCERNING THIS MATERIAL EXCEPT THAT IT CONFORMS TO TREMCO'S PRODUCT SAMPLE. Buyer and user accept the product under those conditions and assume the risk of any failure, injury of person or property and loss or liability resulting from the handling, storage or use of the product, whether or not it is handled, stored, used in accordance with directions or specifications. UNDER NO CIRCUMSTANCE SHALL TREMCO BE LIABLE FOR CONSEQUENTIAL OR INCIDENTAL DAMAGES ARISING FROM ANY BREACH OF WARRANTY. IN ALL CASES, TREMCO'S LIABILITY IS LIMITED, AT TREMCO'S OPTION, TO THE REPLACEMENT OF GOODS, OR THEIR VALUE, PROVEN TO BE DEFECTIVE IN MANUFACTURING.